

Electrochemical performance and carbon resistance comparison between Sn, Cu, Ag, and Rh-doped Ni/ScCeSZ anode SOFCs operated by biogas

Jiang, Zeyu; Snowdon, Abigail; El-Kharouf, Ahmad; Steinberger-Wilckens, Robert

License:

None: All rights reserved

Document Version

Early version, also known as pre-print

Citation for published version (Harvard):

Jiang, Z, Snowdon, A, El-Kharouf, A & Steinberger-Wilckens, R 2020, Electrochemical performance and carbon resistance comparison between Sn, Cu, Ag, and Rh-doped Ni/ScCeSZ anode SOFCs operated by biogas. in *Proceedings of the 14th European SOFC and SOE Forum.*, B0509, European Fuel Cell Forum, Luzern, 14th European SOFC and SOE Forum, Luzern, Switzerland, 20/10/20.

[Link to publication on Research at Birmingham portal](#)

General rights

Unless a licence is specified above, all rights (including copyright and moral rights) in this document are retained by the authors and/or the copyright holders. The express permission of the copyright holder must be obtained for any use of this material other than for purposes permitted by law.

- Users may freely distribute the URL that is used to identify this publication.
- Users may download and/or print one copy of the publication from the University of Birmingham research portal for the purpose of private study or non-commercial research.
- User may use extracts from the document in line with the concept of 'fair dealing' under the Copyright, Designs and Patents Act 1988 (?)
- Users may not further distribute the material nor use it for the purposes of commercial gain.

Where a licence is displayed above, please note the terms and conditions of the licence govern your use of this document.

When citing, please reference the published version.

Take down policy

While the University of Birmingham exercises care and attention in making items available there are rare occasions when an item has been uploaded in error or has been deemed to be commercially or otherwise sensitive.

If you believe that this is the case for this document, please contact UBIRA@lists.bham.ac.uk providing details and we will remove access to the work immediately and investigate.

B0509

Electrochemical performance and carbon resistance comparison between Sn, Cu, Ag, and Rh-doped Ni/ScCeSZ anode SOFCs operated by biogas

Zeyu Jiang, Abigail Snowdon, Ahmad El-kharouf, Robert Steinberger-Wilckens

Centre for Fuel Cell and Hydrogen Research, School of Chemical Engineering

University of Birmingham, B15 2TT Birmingham/UK

ZXJ567@student.bham.ac.uk

Abstract

Ni/ScCeSZ anode-supported SOFCs were fabricated via the reverse tape casting method and an LSCF ($\text{La}_{0.6}\text{Sr}_{0.4}\text{Cr}_{0.2}\text{Fe}_{0.8}\text{O}_3$) cathode was applied. In order to prevent the chemical reaction of zirconia from the electrolyte and strontium from the cathode, a thin barrier layer of $\text{Gd}_{0.1}\text{Ce}_{0.9}\text{O}_{1.95}$ (GDC) was painted on the ScCeSZ electrolyte. On the anode side, Sn, Cu, Ag, and Rh were doped into the Ni-based cermet by infiltration. Metal nitrate hydrates were used as precursors for the dopants. The prepared cells were tested in hydrogen ($\text{H}_2:\text{N}_2=3:1$) and then simulated biogas ($\text{CH}_4:\text{CO}_2:\text{N}_2=2:1:1$) at intermediate operating temperature (600 to 750 °C). The tested cells used ambient air as the oxidant for the electrochemical reactions. The obtained cells were characterised by, scanning electron microscopy (SEM), energy-dispersive X-ray spectroscopy (EDS), X-ray powder diffraction (XRD), and X-ray diffraction (XRD). The electrochemical performance of the prepared cells was characterised by OCV, I-V, operational stability (potentiostatic and galvanostatic), and electrochemical impedance spectroscopy (EIS).

According to our previous work, the carbon accumulation on the anode surface was successfully suppressed by infiltrating Sn, Ag, or Cu into the Ni/YSZ anode-supported cells under biogas operation at 750 °C. The addition of a small amount of Sn or Ag to the Ni/YSZ anodes can greatly improve the electrochemical performance and the operational stability of the cells operated on biogas. Due to the low melting point of Cu, the performance of Cu-Ni/YSZ anodes did not drastically improve. Hence, the Cu-doped Ni/ScCeSZ cells with LSCF cathode are expected to obtain better electrochemical results at slightly lower operating temperature.

1. Introduction

Solid oxide fuel cells (SOFCs) are considered as one of the most promising energy converting electrochemical devices because of their high efficiency of generating electricity from chemical energy. Flexible fuel choice is one of the main advantage of SOFCs because of their high operating temperature. Hence, hydrocarbons can be used as potential fuel for SOFC operation [1]. Ni cermet is the most commonly used anode material for SOFC because of its high catalytic activity towards hydrocarbon reforming. Ni is not only a good catalyst for hydrocarbon-fueled SOFCs, it also promotes carbon forming reactions [2]. Catalyst deactivation can be caused by carbon accumulation, which drastically reduce the electrochemical performance. Furthermore, carbon accumulation can even result in irreversible structural damage of the cell [3, 4]. The main carbon forming reactions in a hydrocarbon-fuelled SOFC are show as follow.



Eq.1 is known as carbon monoxide disproportionation occurring at low temperature (<700 °C) to produced carbon dioxide and carbon, also known as Boudouard reaction [5]. Eq.2 is the reverse reaction of 'water-gas shift' reaction, which also tends to occur at low temperatures. Hydrocarbon dissociation (Eq.3) takes place at high temperatures, which converts hydrocarbon into carbon and hydrogen. [6, 7] Typically, adding external steam or CO₂ and modifying Ni-based anode materials have been extensively investigated to alleviate carbon deposition on the anode. Nevertheless, the existence of excessive amount of H₂O or CO₂ in the fuel dilutes the fuel, resulting in reduced cell performance [2]. Therefore, doping Ni-based anode with metal catalyst or metal oxide can improve cell performance and carbon resistance without fuel dilution [6].

Many studies have reported that noble metal and/or transition metal doping can enhance electrochemical performance and/or reduce carbon deposition of SOFCs operated with hydrocarbons, such as Au [8, 9], Ag [10, 11], Rh [12], Sn [13-15], and Fe [16]. Present work provides a comparison of electrochemical performance and carbon resistance of Sn, Cu, Ag, Rh-doped Ni/ScCeSZ anode SOFCs operated with simulated biogas.

2. Experimental

Cell fabrication – Ni/ScCeSZ anode-supported SOFC button cells used in this study were fabricated using an aqueous tape casting method. Scandia/ceria-stabilised zirconia (10Sc1CeSZ, DAIICHI KIGENSO KAGAKU KOGYO CO), NiO (Green Nickel Oxide, Hart Materials), LSCF (La_{0.6}Sr_{0.4}Cr_{0.2}Fe_{0.8}O₃, Praxair) was used as electrolyte, anode, and cathode material, respectively. A thin barrier layer of Gadolinium-doped ceria (10GDC, Fuel Cell Materials) was applied between the ScCeSZ electrolyte and LSCF cathode to prevent chemical reaction of zirconia and strontium. Details about slurry preparation and cell fabrication process are found in our previous paper [17].

Anode modification – Ni/ScCeSZ anode modification followed the cell fabrication, using Sn, Ag, Cu, and Rh precursors, respectively. The calculated amount of precursor solution was added to the anode surface through a pipette and then dried at ambient temperature. Dopant precursors were further calcined at different temperatures (Table 1) to form metal oxides.

Table 1 – Dopant precursors and their calcination temperatures [10, 18-20].

	Sn	Ag	Cu	Rh
Precursor	SnCl ₂ ·2H ₂ O	AgNO ₃	Cu(NO ₃) ₂ ·3H ₂ O	RhCl ₃ ·xH ₂ O
Calcination temperature (°C)	600	500	400	150

Cell testing and characterisation – Prepared cells were tested in a horizontal furnace setup with two operational mode, hydrogen (21 mL min⁻¹ H₂ and 7 mL min⁻¹ N₂) and biogas (14 mL min⁻¹ CH₄, 7 mL min⁻¹ CO₂ and 7 mL min⁻¹ N₂). Cell testing was conducted at 600 to 750 °C. Silver wire (ScientificWire Company) and silver paste (DAD-87, Shanghai Research Institute of Synthetic Resins) were used as the current collector and sealant, respectively. The SOFC cathode was exposed to the ambient air to provide oxidant for the reaction. Electrochemical characterisations, such as OCV, I-V, potentiostatic, and EIS were carried out by Solartron 1470E and 1455 FRA analysers (Solartron Analytical). For AC impedance measurements, the frequency used was between 0.1 and 10⁶ Hz, with a 10 mV signal amplitude. In order to investigate the surface morphology, surface element distribution, and alloy catalyst crystalline structure, SEM, EDS, and XRD is conducted, respectively. The amount of accumulated carbon on the hydrocarbon-tested cell was determined by temperature-programmed oxidation (TPO).

3. Results

In our previous work, adding 1 wt% of Sn, Ag, and Cu to Ni/YSZ anode showed improved SOFC operational stability under biogas at 750 °C. Enhanced peak power density was only obtained from the Sn-doped Ni/YSZ cell showed. Because of the low melting point of copper and silver, doped Cu and Ag might migrate or agglomerate in the anode scaffold during SOFC operation. Therefore, lower operating temperatures were used to investigate the effect of adding Cu and Ag to the Ni/ScCeSZ cells. Result will be presented at the conference.

References

- [1] B. Hua, M. Li, J.-I. Luo, J. Pu, B. Chi, J. Li, Carbon-resistant Ni-Zr_{0.92}Y_{0.08}O_{2-δ} supported solid oxide fuel cells using Ni-Cu-Fe alloy cermet as on-cell reforming catalyst and mixed methane-steam as fuel, *Journal of Power Sources*, 303 (2016) 340-346.
- [2] P. Boldrin, E. Ruiz-Trejo, J. Mermelstein, J.M. Bermúdez Menéndez, T. Ramírez Reina, N.P. Brandon, Strategies for Carbon and Sulfur Tolerant Solid Oxide Fuel Cell Materials, Incorporating Lessons from Heterogeneous Catalysis, *Chemical Reviews*, 116 (2016) 13633-13684.
- [3] R.J. Gorte, S. Park, J.M. Vohs, C. Wang, Anodes for Direct Oxidation of Dry Hydrocarbons in a Solid-Oxide Fuel Cell, *Advanced Materials*, 12 (2000) 1465-1469.
- [4] H. He, J.M. Hill, Carbon deposition on Ni/YSZ composites exposed to humidified methane, *Applied Catalysis A: General*, 317 (2007) 284-292.
- [5] A. Singh, J.M. Hill, Carbon tolerance, electrochemical performance and stability of solid oxide fuel cells with Ni/yttria stabilized zirconia anodes impregnated with Sn and operated with methane, *Journal of Power Sources*, 214 (2012) 185-194.
- [6] W. Wang, C. Su, Y. Wu, R. Ran, Z. Shao, Progress in Solid Oxide Fuel Cells with Nickel-Based Anodes Operating on Methane and Related Fuels, *Chemical Reviews*, 113 (2013) 8104-8151.
- [7] K. Wei, X. Wang, R.A. Budiman, J. Kang, B. Lin, F. Zhou, Y. Ling, Progress in Ni-based anode materials for direct hydrocarbon solid oxide fuel cells, *Journal of Materials Science*, 53 (2018) 8747-8765.
- [8] I. Gavrielatos, V. Drakopoulos, S.G. Neophytides, Carbon tolerant Ni–Au SOFC electrodes operating under internal steam reforming conditions, *Journal of Catalysis*, 259 (2008) 75-84.
- [9] D.K. Niakolas, J.P. Ouweltjes, G. Rietveld, V. Drakopoulos, S.G. Neophytides, Au-doped Ni/GDC as a new anode for SOFCs operating under rich CH₄ internal steam reforming, *International Journal of Hydrogen Energy*, 35 (2010) 7898-7904.
- [10] Xiaoyan Wu, Xiaoliang Zhou, Yu Tian, Xiaowe Kong, Jun Zhang, Wei Zuo, Xuesong Ye, Kening Sun, Preparation and electrochemical performance of silver impregnated Ni-YSZ anode for solid oxide fuel cell in dry methane, *International Journal of Hydrogen Energy*, 40, 16484-16493, 2015
- [11] X. Wu, X. Zhou, Y. Tian, X. Kong, J. Zhang, W. Zuo, X. Ye, K. Sun, Preparation and electrochemical performance of silver impregnated Ni-YSZ anode for solid oxide fuel cell in dry methane, *International Journal of Hydrogen Energy*, 40 (2015) 16484-16493.
- [12] G.S. Kim, B.Y. Lee, G. Accardo, H.C. Ham, J. Moon, S.P. Yoon, Improved catalytic activity under internal reforming solid oxide fuel cell over new rhodium-doped perovskite catalyst, *Journal of Power Sources*, 423 (2019) 305-315.
- [13] H. Kan, S.H. Hyun, Y.-G. Shul, H. Lee, Improved solid oxide fuel cell anodes for the direct utilization of methane using Sn-doped Ni/YSZ catalysts, *Catalysis Communications*, 11 (2009) 180-183.
- [14] J.-h. Myung, S.-D. Kim, T.H. Shin, D. Lee, J.T.S. Irvine, J. Moon, S.-H. Hyun, Nano-composite structural Ni-Sn alloy anodes for high performance and durability of direct methane-fueled SOFCs, *Journal of Materials Chemistry A*, 3 (2015) 13801-13806.
- [15] L. Troskialina, A. Dhir, R. Steinberger-Wilckens, Improved Performance and Durability of Anode Supported SOFC Operating on Biogas, *ECS Transactions*, 68 (2015) 2503-2513.

- [16] K. Li, L. Jia, X. Wang, J. Pu, B. Chi, L. Jian, Methane on-cell reforming in nickel–iron alloy supported solid oxide fuel cells, *Journal of Power Sources*, 284 (2015) 446-451.
- [17] Z. Jiang, N.A. Arifin, P. Mardle, R. Steinberger-Wilckens, Electrochemical Performance and Carbon Resistance Comparison between Tin, Copper and Silver-Doped Nickel/Yttria-Stabilized Zirconia Anodes SOFCs Operated with Biogas, *Journal of the Electrochemical Society*, 166 (2019) F393-F398.
- [18] R. Al-Gaashani, S. Radiman, N. Tabet, A.R. Daud, Optical properties of SnO₂ nanostructures prepared via one-step thermal decomposition of tin (II) chloride dihydrate, *Materials Science and Engineering: B*, 177 (2012) 462-470.
- [19] J. Ghose, A. Kanungo, Studies on the thermal decomposition of Cu(NO₃)₂ · 3H₂O, *Journal of thermal analysis*, 20 (1981) 459-462.
- [20] W.K. Józwiak, T.P. Maniecki, Influence of atmosphere kind on temperature programmed decomposition of noble metal chlorides, *Thermochimica Acta*, 435 (2005) 151-161.